



CMA Testing and Certification Laboratories

廠商會檢定中心

TEST REPORT

Report No : AU0015622(5)

Date: 17 Mar 2016

Application No : LU008010(9)

Applicant : C4 DEVELOPMENT LTD.
RM 1306, 13/F WINFUL CENTRE,
30 SHING YIP STREET,
KWUN TONG, KOWLOON,
HONG KONG.

Sample Description : One (1) submitted sample stated to be PS Foam.
Test Part(s) : (A) White plastic of foam (PS)



Sample – Test part A

Date Received : 09 Mar 2016

Test Period : 10 Mar 2016 to 17 Mar 2016.

Test Requested : Tests for compliance with U.S. F.D.A. 21 CFR Part 177.1640 (for Polystyrene co-polymer resin in contact with food).

Test Method : With reference to U.S. F.D.A. 21 CFR Part 177.1640.

Test Result : Refer to the result(s) on page 3.

For and on behalf of
CMA Industrial Development Foundation Limited

Authorized Signature : _____

Pun Kwok Yin, Chris
Assistant Manager
Food and Pharmaceutical Division

Page 1 of 3



CMA Testing and Certification Laboratories

廠商會檢定中心

TEST REPORT

Report No : AU0015622(5)

Date: 17 Mar 2016

Application No : LU008010(9)

Conclusion : The requested test(s) of the submitted sample with test part(s) A was (were) found to comply with the respective requirement(s) for the tested items(s) as stated in U.S. F.D.A. 21 CFR Part 177.1640.

For and on behalf of
CMA Industrial Development Foundation Limited

Authorized Signature : _____

Pun Kwok Yin, Chris
Assistant Manager
Food and Pharmaceutical Division

Page 2 of 3



CMA Testing and Certification Laboratories

廠商會檢定中心

TEST REPORT

Report No : AU0015622(5)

Date: 17 Mar 2016

Application No : LU008010(9)

Test Result :

Test Item	Result (% w/w)	Maximum specified limit (not more than)
	A	
Residual Styrene Monomer	<0.05	<ul style="list-style-type: none">• 0.5% (for articles intended for use in contact with fatty foods)• 1.0% (for articles intended for use in contact with non-fatty foods)

- Note :
1. “% w/w” denotes percentage by weight
 2. Maximum specified limit is quoted from U.S. F.D.A. 21 CFR Part 177.1640

***** End of Report *****